

# TEST PARAMETER

CHARACTERISTICS	TEST METHOD	RESULT
Dimension	EN 427	185x1229mm
Thickness-Overall	EN 428	2.5mm
Thickness-Wear Layer	EN 429	0.55mm
Total Weight	EN 430	4.90kg/m <sup>2</sup>
Caster Wheel Chair	EN 425	Pass
Abrasion Resistance	EN 660-2	T grade
Indentation Residual	EN 433	Pass
Colour Fastness	EN ISO 105-BO2	≥6
Fire Rating	EN13501-1	B <sub>fl</sub> -s1
Effects of Stain	EN 423	Pass
Residual Indentation after Stability	EN 434	Shrinkage ≤ 0.08% Curling ≤ 2.0mm
Peeling Strength of Layers	EN 431	Pass
Flexibility-10mm Mandrel	EN 435	No Damage
Resistance to Chemicals	EN 423	Class 0
Toxic	EN 71Part3	Pass
Slip Resistance	DIN 13893	R10
Pendulum Test / Water Wet Slip Potential	EN 14231	PTV36+
Performance Classification	EN 685	23/34/43
GB/T 4085 GB 86t24 B1		Pass
CNS 8907		Pass

Suitable for use with underfloor heating up to 27°C

Wear guarantee:  
Lifetime Residential  
15 Years Commercial





# TEST PARAMETER

**Nordikka**<sup>®</sup>  
— COMMERCIAL LVT —

CHARACTERISTICS	TEST METHOD	RESULT
Dimension	EN 427	185x1229mm
Thickness-Overall	EN 428	2.5mm
Thickness-Wear Layer	EN 429	0.55mm
Total Weight	EN 430	4.90kg/m <sup>2</sup>
Caster Wheel Chair	EN 425	Pass
Abrasion Resistance	EN 660-2	T grade
Indentation Residual	EN 433	Pass
Colour Fastness	EN ISO 105-BO2	≥6
Fire Rating	EN13501-1	B <sub>fl</sub> -s1
Effects of Stain	EN 423	Pass
Residual Indentation after Stability	EN 434	Shrinkage ≤ 0.08% Curling ≤ 2.0mm
Peeling Strength of Layers	EN 431	Pass
Flexibility-10mm Mandrel	EN 435	No Damage
Resistance to Chemicals	EN 423	Class 0
Toxic	EN 71Part3	Pass
Slip Resistance	DIN 13893	R10
Performance Classification	EN 685	23/34/43
GB/T 4085 GB 86t24 B1		Pass
CNS 8907		Pass

Suitable for use with underfloor heating up to 27°C

Wear guarantee:

Lifetime Residential

15 Years Commercial

